

TECHNICAL DATA SHEET

Technical Specifications	Unit	Galaxy Metallic 110gsm (One side)	Galaxy Metallic 120gsm (Double side)	Galaxy Metallic 250gsm (Double side)	Galaxy Metallic 300gsm (Double side)
Grammage	g/m ²	110 ± 5	120 ± 6	250 ± 12	300 ± 15
Water Content	%	8 ± 2	8 ± 2	8 ± 2	8 ± 2
Thickness	mm	0,14 ± 0,01	0,15 ± 0,01	0,32 ± 0,02	0,40 ± 0,02
Water Absorbency	g/m ²	≤ 50	≤ 50	≤ 50	≤ 50
Folding endurance	times	≥ 20	≥ 20	≥ 10	≥ 10
Tearing Strength	mN.	≥ 600	≥ 600	≥ 1600	≥ 2200
Burst Index	Kpa.m ² /g	≥ 1.5	≥ 1.5	≥ 1.5	≥ 1.5
Smoothness	S	≥ 10	≥ 10	≥ 7	≥ 7
Stifness	mN.m			≥ 3.0	≥ 5.0

Remarks :

*** Grades, colors and range of products are subject to change. Due to different batch of makings this paper variations in shade and surface and speck count may sometimes occur. ***

*** The specifications are the property of the above TPG (HK) LTD and may be changed without prior notice. They are target values only for is as a guide. ***