

## TECHNICAL DATA SHEET

### Scheda Tecnica

Mod. PG 7.06-01 rev.3 del 18/03/10

|   |   |
|---|---|
| <b>Product</b><br><b>GLAM CHAMPAGNE</b> | <b>Weight</b><br><b>120 g/m<sup>2</sup></b> |
|---|---|

| Characteristic                        | Internal Method | Standard Reference | Unit of Measure  | Side or Direction | Specific Values | Tolerance 2σ |
|---------------------------------------|-----------------|--------------------|------------------|-------------------|-----------------|--------------|
| <b>Substance</b>                      | PO 301          | ISO 536            | g/m <sup>2</sup> | -                 | 120,0           | ± 5%         |
| <b>Thickness</b>                      | PO 303          | ISO 534            | µm               | -                 | 152,0           | ± 5%         |
| <b>Absolute Humidity</b>              | PO 302          | ISO 287            | %                | -                 | 6,0             | ± 1,0        |
| <b>L&amp;W Stiffness (15°/ 10 mm)</b> | PO 323          | ISO 2493           | mN               | MD                | 200             | min          |
| <b>L&amp;W Stiffness (15°/ 10 mm)</b> | PO 323          | ISO 2493           | mN               | CD                | 100             | min          |
| <b>Roughness Bendtsen</b>             | PO 309          | ISO 8791-2         | ml/min           | -                 | 300             | ± 100        |

The technical data sheet shall be deemed accepted if not challenged within one month of receipt.

|                           |                   |
|---------------------------|-------------------|
| <b>Emission Date</b>      | 01/02/2020        |
| <b>TDS n°</b>             | 05AGM             |
| <b>Period of Validity</b> | Until next review |
| <b>R&amp;S Manager</b>    | Renato Burba      |

Our internal methods are based upon the indicated official methods, but could differ in some details. The above data have been agreed in good faith and tested to the best of our knowledge, but we cannot guarantee the results of further reprocessing that are beyond our control.

We recommend that the Clients, in all cases, evaluate if the characteristics of our paper fit their actual needs and the requirements of the final products.

## TECHNICAL DATA SHEET

### Scheda Tecnica

Mod. PG 7.06-01 rev.3 del 18/03/10

|   |   |
|---|---|
| <b>Product</b><br><b>GLAM CHAMPAGNE</b> | <b>Weight</b><br><b>250 g/m<sup>2</sup></b> |
|---|---|

| Characteristic                        | Internal Method | Standard Reference | Unit of Measure  | Side or Direction | Specific Values | Tolerance 2σ |
|---------------------------------------|-----------------|--------------------|------------------|-------------------|-----------------|--------------|
| <b>Substance</b>                      | PO 301          | ISO 536            | g/m <sup>2</sup> | -                 | 250,0           | ± 5%         |
| <b>Thickness</b>                      | PO 303          | ISO 534            | μm               | -                 | 305,0           | ± 5%         |
| <b>Absolute Humidity</b>              | PO 302          | ISO 287            | %                | -                 | 6,0             | ± 1,0        |
| <b>L&amp;W Stiffness (15°/ 10 mm)</b> | PO 323          | ISO 2493           | mN               | MD                | 200             | min          |
| <b>L&amp;W Stiffness (15°/ 10 mm)</b> | PO 323          | ISO 2493           | mN               | CD                | 100             | min          |
| <b>Roughness Bendtsen</b>             | PO 309          | ISO 8791-2         | ml/min           | -                 | 300             | ± 100        |

The technical data sheet shall be deemed accepted if not challenged within one month of receipt.

|                           |                   |
|---------------------------|-------------------|
| <b>Emission Date</b>      | 01/02/2020        |
| <b>TDS n°</b>             | 05BGM             |
| <b>Period of Validity</b> | Until next review |
| <b>R&amp;S Manager</b>    | Renato Burba      |

Our internal methods are based upon the indicated official methods, but could differ in some details. The above data have been agreed in good faith and tested to the best of our knowledge, but we cannot guarantee the results of further reprocessing that are beyond our control.

We recommend that the Clients, in all cases, evaluate if the characteristics of our paper fit their actual needs and the requirements of the final products.