



# ZHEJIANG GANGLONG NEW MATERIAL CO., LTD

MAQIAO WARP KNITTING SCIENCE & TECHNOLOGY INDUSTRIAL ZONE

HAINING ZHEJIANG CHINA, 314419

## TECHNICAL DATA SHEET

### SCRIMLESS PET GREY BACK

Item	Unit	Value	Test Method
<b>Support Base</b>	Polyethylene Terephthalate (PET)		
<b>Thickness of PET</b>	Micron	125	/
<b>Coating</b>	PVC & Grey PVC		
<b>Total weight</b>	Gsm/m <sup>2</sup>	420±20	DIN53352 BS3424 Method5A
<b>Total Thickness</b>	mm	0.30±0.02	
<b>Width</b>	m	0.914, 1.06, 1.27, 1.37, 1.52, 1.60, 2.20, 250, 3.20	
<b>Temperature Resistance</b>	°C	-20~70	DIN53357 BS3425 Method10
<b>Flammability</b>	Can be apply for B1, B2 and NFPA701		
<b>LOW CADMIUM &amp; HEAVY METALS</b>	We can be applied for : Cadmium free (EN71-3) or Reach Compliance		
<b>Ink Printability</b>	Solvent, Eco-solvent, UV and Screen printing		
<b>Advantages:</b>	<ul style="list-style-type: none"><li>◆Non-curling at the edge and lay-flat appearance</li><li>◆Super smooth surface for high resolution printing.</li><li>◆Excellent printing performance.</li><li>◆Comparing to water-based inkjet media, print direct to substrate, no lamination needed.</li></ul>		
<b>Applications</b>	<ul style="list-style-type: none"><li>◆Display system, Roll-up, Pop-up, X-Banner, Scrolling banner.</li><li>◆Trade shows and Event Graphics</li><li>◆Any hanging banner and sign applications</li></ul>		
<b>Conclusions and Announcements</b>	Declaration by GLP: Please choose GLP products suitably according to relative provisions or industrial standards. GLP bears the responsibility for the specified technical and performance data on this page only. GLP is not responsible for any other liability. (The technical data on this page is calculated on average, and ±5% tolerance is acceptable)		